

AMENDED CLAIMS

[received by the International Bureau on 24 July 2000 (24.07.00) ; original claims 1-14 replaced by new claims 1-14 (2 pages)]

1. A self-sustaining film comprising a composition including an acrylic resin base containing a quaternary ammonium compound in an amount of about 1 to about 10 wt % based on the weight of the composition to impart a static dissipative property and a conductive property to said film.

2. The self sustaining film of claim 1, wherein said acrylic resin is a methylmethacrylate containing polymer.

3. The self sustaining film of claim 1, further comprising a dispersion of zinc oxide particles.

4. The self sustaining film of claim 1, further comprising a polyethylene wax emulsion.

5. A paper layer coated with a conductive polymeric composition comprising an acrylic resin base containing a quaternary ammonium compound in an amount of about 1 to about 10 wt % based on the weight of the composition to impart a static dissipative property and a conductive property to said paper layer.

6. The paper layer of claim 5, wherein the said acrylic resin is a methylmethacrylate containing polymer.

7. The paper layer of claim 5, further comprising a dispersion of zinc oxide particles.

8. The paper layer of claim 5, further comprising a polyethylene wax emulsion.

9. A laminate comprising two or more laminae coated on at least one surface of a laminae with a conductive polymeric composition comprising an acrylic resin base containing a quaternary ammonium compound in an amount of about 1 to about 10 wt % based on the weight of the composition to impart a static dissipative property and a conductive property to said laminate.

Handwritten signature and vertical stamp: 00004485 022204

Lu
B1

10. A package comprising a layer of a conductive polymeric composition comprising a composition including an acrylic resin base containing a quaternary ammonium compound in an amount of about 1 to about 10 wt % based on the weight of the composition to impart a static dissipative property and a conductive property to said polymeric composition, in combination with a material selected from the group consisting of paper, fabric, non-woven material and combinations thereof.

11. The package of claim 10, wherein said at least one material further comprises a metallized surface.

12. The package of claim 10, wherein the material is paper.

13. The package of claim 12, further comprising a dispersion of zinc oxide particles.

14. The package of claim 12, further comprising a polyethylene wax emulsion.

FORWARDED SHEET
Lu
Cl